



Shanghai Suo Shi Chemical Industrial Co.Ltd

Dongguan Suoshi New Material Co.,Ltd

Factory Address: No.66,baizhoubain,guanlongRoad, dongcheng District, dongguan
City, guandongProvince, China

TEL: 0769-22653892

FAX: 0769-22653316

Version: May.28.2015

Crack texture agent MCC (TDS)

一、 Description: Dry-blending MCC 0.5-1% with base wrinkle-powder can be formed regular shell-like effect floating on wrinkle powder.

二、 technical indicators:

Appearance : white powder

Soft range: 110~120°C

Solid content : >99%

Bulk density: 500~600g/L

三、 reference formula

epoxy	700	polyurethane	600
polyester	15-20	1174 Cross-link agent	36
Dicy	28	32-18A Catalyst	9. 5
MCD	32	Flow additive	2 - 4
Flow additive	2 - 4	BaSO4	350
pigment	220	pigment	//
base coat /MCC=100/0.5~1			

四、 Remark

1. If you dry-blending with MCC, please control the time of mixing, too long time is not good choice, sieve it after dry-blending is inadvisable.
2. Wrinkling size can be adjusted by base formulation and MCC usage
3. Adding in 0.1%-0.3% floating wrinkle agent to enhance product stability and three-dimensional of the film

五、 **Packaging and storage:** Polyethylene lining, net weight 25KG caveat; stored in a cool and dry place to avoid moisture absorption. In the < 30 °C is valid for two years at room temperature.