



Shanghai Suo Shi Chemical Industrial Co.Ltd

Dongguan Suoshi New Material Co.,Ltd

Factory Address: No.66 Yong Wei Road ,Bai Zhou edge,Guan Long Road,  
Dong Cheng District, Dong guan City,Guangdong  
Province , China

TEL: 0769-22653892

FAX: 0769-22653316

Version: Nov. 18, 2022

## Dry flow additive T-935

### 1.Description

Proper addition of dry powder flowing agent can improve the porosity and leveling of powder, improve the phenomenon of powder spitting and gun blocking during powder spraying, and improve the powder rate in dead corner ; Especially suitable for metal and pearlescent powder coating systems. The particle size of T-935 is finer than that of T-933, and the effect is more obviously.

### 2.Typical physical data

Appearance	white fine powder
PSD(um)	135~145 $\mu$ m
Solid content(%)	>99%

### 3.Method and dosage

0.3~0.5% of total powder be added in base together before bonding

### 4.Package and storage:

Packaging with PE lined Kraft paper bags, Net weight 10kg per bag. Store in cool and dry place to avoid moisture. According to our experience, the shelf life of this product is at least 2 years when ambient temperature below 30  $^{\circ}$ C.